DNV·GL

Certificate No:
TAE00003TT

TYPE APPROVAL CERTIFICATE

This is to certify:

That the Low Voltage Cable

with type designation(s)
CKJ82/NA, CKJ92/NA, CKJP82/NA, CKJP92/NA, CKJ85/NC, CKJ86/NC, CKJ95/NC, CKJ96/NC, CKJP85/NC, CKJP86/NC, CKJP95/NC, CKJP96/NC, CHJ82/NA, CHJP82/NA, CHJ85/NSC, CHJ86/NSC, CHJP85/NSC, CHJP86/NSC, CHJP1 85/NSC, CHJP1 86/NSC, CHJP1 95/NSC, CHJP1 96/NSC,

Issued to
Dalian Yongxu Wire & Cable Manufacturing Co., Ltd
Dalian, China

is found to comply with
DNV GL rules for classification – Ships, offshore units, and high speed and light craft

Application :

Product(s) approved by this certificate is/are accepted for installation on all vessels classed by DNV GL.
Rated voltage (V) 150/250
Temp. class (°C) 90

Issued at **Hamburg** on **2019-11-26**
This Certificate is valid until **2024-11-25**.
DNV GL local station: **Dalian**

for **DNV GL**

Approval Engineer: **Carsten Hunsalz**

Arne Schaarmann
Head of Section

This Certificate is subject to terms and conditions overleaf. Any significant change in design or construction may render this Certificate invalid.
The validity date relates to the Type Approval Certificate and not to the approval of equipment/systems installed.

© DNV GL 2014. DNV GL and the Horizon Graphic are trademarks of DNV GL AS.

Product description

XLPE insulated shipboard control and instrumentation cables

Rated voltage:	150/250 V
Maximum operating conductor temperature:	90° C
Conductor:	Tinned stranded copper, class 2
Insulation:	Mica tape + XLPE
Individual screen:	P - Tape or copper wire braid; P1 - Al/polyester tape
Inner covering:	Extruded for cables with galvanized steel wire braid
Armour / braid:	8 - Copper wire braid 9 - Galvanized steel wire braid
Outer sheath:	2 - ST2, 5 - SHF2, 6 - SHF1

CHJ cable types:

No. of pair units:	Nominal cross section mm²
1 – 48	0.5, 0.75, 1, 1.5, 2.5

CKJ cable types:

No. of cores:	Nominal cross section mm²
2 - 37	0.75, 1, 1.5, 2.5

Application/Limitation

Control and instrumentation.

This type of cable is fire resistant in accordance with IEC Publication 60331.

The requirements of SOLAS Amendments Chapter II-1, Part D, Reg. 45, 5.2 (provision to be taken to limit Fire Propagation along Bunches of Cables or Wires) are fulfilled without any additional measures.

The following applies to NSC / NC type cables only:

Fire resistant. Flame retardant Cat. A. Halogen free. Low smoke.

Type Approval documentation

Test report :	No. 1e - 3e; ID. No. 080122 No. CT07-1607-5 No. 2013400303006011500, dated 2013-12-20 No. 2013400303006011501, dated 2013-12-20

Tests carried out

Standard	Release	General description	Limitation
IEC 60092-350	2014-08	General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications	
IEC 60092-376	2017-05	Cables for control and instrumentation circuits 150/250 V (300 V)	
IEC 60092-360	2014-04	Electrical installations in ships - Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation and telecommunication cables.	

Standard	Release	General description	Limitation
IEC 60332-3-22	2018-07	Tests on electric and optical fibre cables under fire conditions – Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A	Charred portion of sample does not exceed 2,5m above bottom edge of burner.
IEC 60331-1	2018-03	Fire resistance / Circuit integrity – Test method for fire with shock at temperature of at least 830ºC for cables rated up to and including 0,6/1 kV	For cables with an overall diameter exceeding 20 mm
IEC 60331-2	2018-03	Fire resistance / Circuit integrity – Test method for fire with shock at temperature of at least 830ºC for cables rated up to and including 0,6/1 kV	For cables with an overall diameter not exceeding 20 mm
IEC 60754-1**	2011-11	Test on gases evolved during combustion of materials from cables - Part 1: Determination of the halogen acid gas content	Low Halogen: <0,5% Halogen
IEC 60754-2**	2011-11	Test on gases evolved during combustion of materials from cables - Part 2: Determination of acidity (by pH measurement) and conductivity	Halogen free: pH > 4,3 Conductivity < 10µS/mm
IEC 60684-2**	2011-08	Clause 45.2 Methods of determination of low levels of fluorine	Fluorine content < 0,1%
IEC 61034-1/2**	2013-06	Measurement of smoke density of cables burning under defined conditions – Test apparatus, procedure and requirements	Low smoke Light transmittance >60%

** NSC / NC type only

Marking of product

Example:

Dalian Yongxu Wire & Cable Manufacturing Co., Ltd - CHJ85/NSC – 150/250V – size - IEC 60332-3-22 - IEC 60331-1/2 - Lot no.

Periodical assessment

The scope of the periodical assessment is to verify that the conditions stipulated for the Type approval are complied with and that no alterations are made to the product design or choice of materials.

The main elements of the assessment are:

- Inspection on factory samples, selected at random from the production line (where practicable)
- Results from Routine Tests (RT) checked (if not available tests according to RT to be carried out)
- Review of type approval documentation
- Review of possible change in design, materials and performance
- Ensuring traceability between manufacturer's product type marking and Type Approval Certificate.

Periodical assessment is to be performed after 2 years and after 3.5 years. A renewal assessment will be performed at renewal of the certificate.
END OF CERTIFICATE