

TYPE APPROVAL CERTIFICATE

This is to certify:**That the Sacrificial Anode Material for Corrosion Protection**with type designation(s)
Galvalum III

Issued to

Cathodic Protection Technology Pte Ltd
SINGAPORE, Singapore

is found to comply with

DNV GL class programme DNVGL-CP-0107 – Type approval – Sacrificial anode materials
DNV GL rules for classification – Ships
Det Norske Veritas' Recommended Practices, DNV-RP-B401 Cathodic Protection Design**Application :****The mean current capacity of the sacrificial anode material after 12 months free running testing is 2621 Ah/kg, the mean closed circuit potential is about -1070 mV vs. Ag/AgCl seawater. The approval is given for use in seawater at temperatures below 30°C.****Product(s) approved by this certificate is/are accepted for installation on all vessels classed by DNV GL.**This Certificate is valid until **2021-07-26**.Issued at **Høvik** on **2016-07-27**DNV GL local station: **Singapore**Approval Engineer: **Gisle Hersvik**for **DNV GL****Arnstein Gloppen**
Head of Section

This Certificate is subject to terms and conditions overleaf. Any significant change in design or construction may render this Certificate invalid.
The validity date relates to the Type Approval Certificate and not to the approval of equipment/systems installed.

Job Id:
Certificate No: **TAS00000KK**

Product description

Galvalum III; Sacrificial Aluminium Alloy Anode Material for Corrosion Protection.

Manufactured by

Cathodic Protection Technology (Johor) Sdn Bhd, PLO 126 Kawasan Perindustrian Senai, Phase III
81400 Senai, Johor, Malaysia

DNV GL local office: Singapore

Responsibility

The Company (stated on the front page of this Certificate) takes the responsibility that both design and production are in compliance with Rules, Standards and/or Regulations listed on page 1 of this certificate.

Application/Limitation

Approval is given for the sacrificial anode material; not for anode design.

The mean current capacity of the sacrificial anode material after 12 months galvanostatic control testing is **2621** Ah/kg. The mean closed circuit potential is -1,07 V vs. Ag/AgCl/Seawater. The mean anode current density was measured to approx. 0,7 A/m².

The recommended design electrochemical capacity for aluminium based alloys in seawater is 2000 Ah/kg (ref. DNV-RP-B401).

The approval is given for use in seawater at temperatures below 30°C.

Type Approval documentation

Tests carried out

Type Testing carried out according to **Type Approval documentation**.

Testing has been performed with basis in DNV-RP-B401 (1993) and NORSOK M-503, Cathodic protection (Rev. 2, Sept. 1997).

Marking of product

Product shall be marked with *manufacturer's name*; **C.P. TECH** and *type designation*; **N** (indicating **Galvalum III**).

The marking is to be carried out in such a way that it is visible, legible and indelible. The marking of product is to enable traceability to the DNV GL Type Approval Certificate.

Periodical assessment

The scope of the Periodical Assessment is to verify that the conditions stipulated for the Type Approval is complied with and that no alterations are made to the product design or choice of materials.

Periodical Assessment to be performed after 2 years (Certificate Retention) and at renewal after 5 years (Certificate Renewal).



Job Id:
Certificate No: **TAS00000KK**

The main elements of the Periodical Assessment are to:

- Ensure that **Type Approval documentation** is available.
- Review design, materials, production process, and performance with respect to possible changes, in order to ensure compliance with **Type Approval documentation** and/or referenced material specifications.
- Ensure traceability between manufacturer's product marking and the DNV GL Type Approval Certificate.

END OF CERTIFICATE